



QUALITY MANAGEMENT SYSTEM

UR.17-SD-U1731.0

REVISION NO

PAGE

6

1/1

EH 241 POLYPROPYLENE PRODUCT SPECIFICATION

TRADE NAME : PETOPLN EH 241

GUARANTEED VALUES :

TESTS	UNIT	VALUE	METHOD
Melt Flow Rate (MFR) (230°C / 2.16 kg)	g/10min	20 - 28	ASTM D-1238
Contamination, 100 g	pcs	Max. 10	TM-113

TYPICAL VALUES :

Tensile Strength - at Yield	kg/cm ²	365	ASTM D-638
Colour, b-value (10D65)	-	1.5	Hunter Lab. CQ

PRODUCT SHAPE : Pellets

PACKING : In 25 kg FFS (Form Fill Seal) white colored PE bags
or 1400 kg big-bags

STORAGE CONDITIONS : In closed and dry areas, sheltered from direct sun light

APPLICATION : Suitable for very rapid injection moulding applications.
General purpose injection and fibre grade.
(plastic goods, toys, fibres)

MSDS NO : UR.17-BF-00015-ING

NOTE: Typical values are the average results of the analyses made in Petkim's laboratories, provided for information only. They are not guaranteed values.

This grade has certificate for production of the material in contact with foodstuffs as received by Ministry of Agriculture and Rural Affairs dated 21.02.2007 and no. 35-00186-0006-7.