

EH 251 POLYPROPYLENE PRODUCT SPECIFICATION**TRADE NAME : PETOPL EN EH 251****GUARANTEED VALUES :**

<u>TESTS</u>	<u>UNIT</u>	<u>VALUE</u>	<u>METHOD</u>
Melt Flow Rate (MFR) (230°C / 2.16 kg)	g/10min	20 - 28	ASTM D-1238
Contamination, 100 g	pcs	Max. 10	TM-113

TYPICAL VALUES :

Tensile Strength - at Yield	kg/cm ²	350	ASTM D-638
Colour, b-value (10D65)	-	1.9	Hunter Lab. CQ

PRODUCT SHAPE : Pellets**PACKING : In 25 kg FFS (Form Fill Seal) white colored PE bags
or 1400 kg big-bags****STORAGE CONDITIONS : In closed and dry areas, sheltered from direct sun light****APPLICATION : Suitable for very rapid injection moulding applications.
General purpose injection and fiber grade.
(plastic goods, toys, fibres)****MSDS NO : UR.17-BF-00015-ING****NOTE: Typical values are the average results of the analyses made in Petkim's laboratories, provided for information only. They are not guaranteed values.****This grade has certificate for production of the material in contact with foodstuffs as received by Ministry of Agriculture and Rural Affairs dated 21.02.2007 and no. 35-00186-0006-7.**